

ENERTITE® G LOW-DENSITY, OPEN-CELL INSULATION

enertite
Open-Cell Spray Polyurethane Foam Insulation



DESCRIPTION:

ENERTITE G is a two-component low-density open-cell spray polyurethane foam system designed for use in residential construction and common commercial insulation applications. **ENERTITE G** is compatible with most common construction materials, but can only be processed with ELASTOSPRAY® 8000A Isocyanate. The benefits of **ENERTITE G** include:

- Superior insulation
- Non-fibrous
- Sound control

TYPICAL PROPERTIES⁽¹⁾:

PROPERTY	METHOD	ENERTITE G
Resin:		
Specific Gravity @ 70°F	ASTM D 1638	1.135
Viscosity @ 77°F (cps)	Brookfield	350
Cured Foam:		
Density, core (pcf @ 4" lifts)	ASTM D 1622	0.5 (nominal)
Open Cell Content (%)	ASTM D 6226	>90
Thermal Resistance (aged) R-value (ft ² hr °F/Btu in) ⁽²⁾	ASTM C518	3.9 / in @ 1-in thick 3.7 / in @ 4-in thick
Response to Thermal and Humid Aging (% linear change)		
158°F / 97% RH / 168 hrs	ASTM D 2126	< -2.0
Water Absorption (vol %)	ASTM D 2842	> 40%
Tensile Strength	ASTM D 1623	5.9 psi
Water Vapor Transmission – 3.5-in foam thickness		
Permeability (Perm-inch)	ASTM E 96	59 (Calculated)
Permeance (Perm)	ASTM E 96	16.9
Surface Burning Characteristics		
Flame Spread Index ⁽³⁾	ASTM E 84	≤ 25
Smoke Developed Index	ASTM E 84	≤ 450

(1) These physical property values are typical for this material as applied at our development facility under controlled conditions. SPF performance and actual physical properties will vary with differences in application (i.e. ambient conditions, process equipment and settings, material throughput, etc.). As a result, these published properties should be used as guidelines solely for the purpose of evaluation. Physical property specifications should be determined from actual production material.

The above data was collected from samples prepared using equipment configurations pertinent to lab conditions. Parameters can be obtained upon request by calling 800-706-1712.

(2) The data chart shows the R-value of this insulation. "R" means resistance to heat flow. The higher the R-value, the greater the insulating power. Compare insulation R-values before you buy. There are other factors to consider. The amount of insulation will depend upon the climate, the type and size of your house, and the fuel use patterns and family size. If you buy too much insulation it will cost you more than what you will save on fuel. To achieve proper R-values, it is essential that this insulation be installed properly.

(3) This numerical flame spread rating does not reflect hazards presented by this or any other material under actual fire conditions. Polyurethane foam systems should not be left exposed and must be protected by a minimum 15-minute thermal barrier or other code-compliant material as allowed by applicable building code(s) and Code Officials. Building Codes provide guidelines representing minimum requirements. Further information is available at www.iccsafe.org. Consult all Authorities Having Jurisdiction (AHJ) over an area for additional or specific requirements prior to beginning any project.

ADDITIONAL TESTING, APPROVALS & CERTIFICATIONS:

- ASTM E 84 (Class I) with Product Listing^{(3) (4)}
- NFPA 285 complying assemblies available
- Fire Resistant assemblies available
- INTERTEK Code Compliance Research Report CCRR-1032
- Thickness is not limited when installed behind a code-prescribed thermal barrier (per ICC-ES AC377)
- Approved for certain Attic & Crawl Space installations with and without prescriptive ignition barriers per ICC-ES AC377, Appendix A1.2.2 and Appendix X

CRITICAL RADIANT FLUX (attic insulation)

PROPERTY	METHOD	ENERTITE G
Critical Radiant Flux, 4-in foam thickness	ASTM E970	0.26 W/cm ²
Critical Radiant Flux, 6-in foam thickness	ASTM E970	0.25 W/cm ²

AIR LEAKAGE

PROPERTY	METHOD	ENERTITE G
Air Leakage, 3.5-in foam thickness (L/s·m ² @ 75 Pa ΔP)	ASTM E 283	<0.02 L/s·m ²

- GREENGUARD and GREENGUARD Gold Certification for VOC emissions
- Meets the requirements of CDPH Section 01350 for VOC emissions and formaldehyde
- Mold resistant per ASTM C1338 – "Pass" rating (no growth)

ADDITIONAL INFORMATION:

Odor level of spray polyurethane foam is dependent on proper application using the recommended processing parameters and proper ventilation.

Caution - Failure to follow the application precautions, safety data sheet information as well as accepted industry practices (www.spraypolyurethane.org) may result in unwanted foam physical properties and applications that may not provide the desired results. This also includes unwanted health risks such as possible respiratory issues, sensitization or eye irritations such as blue haze for applicators and workers located in the area being sprayed. A full understanding of the foam processing and all safety risks must be completed before spraying. Call our BASF spray foam team if you have questions 800-706-0712.

Please contact your local Sales or Technical Representative for specific questions regarding **ENERTITE G** properties, approvals, or certifications.

(4) ASTM E 84 is a test designed for sample thickness up to four (4) inches. NFPA 286 is a building code recognized alternative test conducted on large-scale assemblies to evaluate foam thickness in excess of four (4) inches as permitted in 2012 IBC Section 2603.10; 2006 & 2009 IBC Section 2603.9; 2009 & 2012 IRC Section R316.6; 2006 IRC Section R314.6.



ENERTITE® G LOW-DENSITY OPEN-CELL INSULATION

GENERAL INFORMATION:

ENERTITE G is a spray polyurethane foam (SPF) system intended for installation by qualified contractors trained in the processing and application of SPF systems, as well as the plural-component polyurethane dispensing equipment required to do so. Contractors and applicators must comply with all applicable and appropriate storage, handling, processing and safety guidelines. BASF technical service personnel should be consulted in all cases where application conditions are questionable.

ENERTITE G has an estimated theoretical yield range of 17,000-21,000 board feet per set. Actual yield performance can be in excess of or below the referenced estimated theoretical range based on factors affecting density including, however, not limited to: multiple lifts, spray pass thickness, substrate texture, substrate temperature, overspray loss, windy conditions, altitude, container residue, equipment characteristics & temperatures, applicator technique, etc. For help estimating yield for this and other spray foams, please consult Spray Polyurethane Foam Alliance's SPFA-121 SPF Estimating Reference Guide.

CAUTIONS AND RECOMMENDATIONS:

ENERTITE G is designed for an application rate of ½ inch minimum to 6 inches maximum per pass. Once installed and material has cooled, it is possible to add additional applications in order to increase the overall installed thickness of SPF. Thicker installations are allowed based on large scale testing. Please see ESR-3102 for additional information. This application procedure is in compliance with the Spray Polyurethane Foam Alliance (SPFA).

ENERTITE G is NOT designed for use as an EXTERIOR roofing system. BASF offers a separate line of products for exterior roofing applications. For more information, please contact your sales representative.

Cold-storage structures such as coolers and freezers demand special design considerations with regard to thermal insulation and moisture-vapor drive. ENERTITE G should NOT be installed in these types of constructions unless the structure was designed by a design professional for specific use as cold storage.

ENERTITE G is designed for installation in most standard construction configurations using common materials such as wood and wood products, metal and concrete. ENERTITE G has performed successfully when sprayed onto wood substrates down to 20°F and can be used in colder temperatures using special cold weather application guidelines. For cold weather applications and when spraying onto heat sink-materials such as metal or concrete, ENERTITE G can be sprayed using a flash pass method to enhance adhesion. BASF recommends the use of mock ups or test spray areas before starting the full-scale project to evaluate material performance in current conditions, as well as to ensure proper processing is occurring to create a suitable finished product.

Climate	A side, B side, Hose Temp (Adjust in +/- 5° increments)	Proportioner set pressure (Spraying pressure)
Colder	125°F – 135°F	1150 – 1450 psi (900 – 1200 psi)
Warmer	105°F – 125°F	1150 – 1450 psi (900 – 1200 psi)

Foam plastic materials installed in walls or ceilings may present a fire hazard unless protected by an approved, fire-resistant thermal barrier with a finish rating of not less than 15 minutes as required by building codes. Rim joists/header areas, in accordance with the IRC and IBC, may not require additional protection. Foam plastic must also be protected against ignition by code prescribed or properly tested materials in attics and crawl spaces. See relevant Building Codes and www.iccsafe.org for more information.

In addition to reading and understanding the SDS, all contractors and applicators must use appropriate respiratory, skin and eye Personal Protective Equipment (PPE) when handling and processing polyurethane chemical systems. Personnel should review the following documents published by Spray Polyurethane Foam Alliance (SPFA): AX-171 Course 101-R Chapter 1: Health, Safety and Environmental Aspects of Spray Polyurethane Foam and Coverings www.spraypolyurethane.org

Also, the following document is available from the Center for the Polyurethanes Industries (CPI): *Model Respiratory Protection Program for Compliance with the Occupational Safety and Health Administration's Respiratory Protection Program Standard 29 C.F.R. §1910.134*

As with all SPF systems, improper application techniques should be avoided. Examples of improper application techniques include, but are not limited to excessive thickness of SPF, off-ratio material and spraying into or under rising SPF. Potential results of improperly installed SPF include: dangerously high reaction temperatures that may result in fire and offensive odors that may or may not dissipate. Improperly installed SPF must be removed and replaced with properly installed materials.

LARGE MASSES of SPF should be removed to an outside safe area, cut into smaller pieces and allowed to cool before discarding into an appropriate trash receptacle.

All areas that are sprayed incorrectly or result in A only material, B only material, improperly mixed or off ratio materials, too thick of an application or two quick of a thickness build up, are to be removed and replaced with properly processed spray foam. All cleaning solvents and others materials are to be captured and properly disposed of and not left at the job site.

SPF insulation is combustible. High-intensity heat sources such as welding or cutting torches must not be used in contact with or in close proximity to ENERTITE G or any polyurethane foam. The insulation must not be used in areas that have a maximum service temperature greater than 180°F(82°C).

SHELF LIFE AND STORAGE CONDITIONS:

ENERTITE G has a shelf life of approximately Six (6) months from the date of manufacture when stored in original, unopened containers at 50-80°F. As with all industrial chemicals, this material should be stored in a covered, secure location and never in direct sunlight. Storage temperatures above the recommended range will shorten shelf life. Storage temperatures above the recommended range may also result in elevated headspace pressure within packages.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY:

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. Customer assumes full responsibility for quality control, testing and determination of suitability of products for its intended application or use. We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose. Our total liability and customers' exclusive remedy for all proven claims is replacement of nonconforming product and in no event shall we be liable for any other damages.

While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be used without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the description, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Warning: These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.